



Au service des professionnels

TECHNICAL DATA SHEET MANUEL STRETCH FILM

Ref FPAL _ film palettisation manuel transparent _ code EAN 3760082 800017

Ref FPALNOIR _ film palettisation manuel noir _ code EAN 3760082 800031

TEST NO:	TEST METHOD	PROPERTY	UNIT	TYPICAL VALUE		
1	BenchMark	Film Thickness	mic	12	15	17
2	ASTM D 882	Load At Yield (MD)	N/Inch	>1.5	>1.7	>2.0
3	ASTM D 882	Load At Yield (TD)	N/Inch	>1.0	>1.1	>1.2
4	ASTM D 882	Tensile Stre.Ultimate(MD)	N/Inch	46	46	48
5	ASTM D 882	Tensile Stre. Ultimate(TD)	N/Inch	19	20	20
6	ASTM D 882	Ultimate Elongation(MD)	%	350	425	450
7	ASTM D 882	Ultimate Elongation(TD)	%	725	750	775
8	ASTM D 2578	Stretch ability	%	>100	>120	>150

Dimensions 450mm X 17 mμ

Tolérances de production

Longueur +/- 3 %

Epaisseur +/- 5 %

Largeur +/- 1%

Colis de 6

Palette de 48 colis (3X16)

Dernière mise à jour, le 21/03/2019

Le service qualité

France Alu Film